

JC09 Rec'd PCT/PTO 01 MAR 2001

FORM PTO-1390 (Modified)  
(REV 11-98)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES  
DESIGNATED/ELECTED OFFICE (DO/EO/US)  
CONCERNING A FILING UNDER 35 U.S.C. 371

13929/122995

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/786189

INTERNATIONAL APPLICATION NO  
PCT/EP99/06390INTERNATIONAL FILING DATE  
August 31, 1999PRIORITY DATE CLAIMED  
September 1, 1998

TITLE OF INVENTION

BIODEGRADABLE COMPOSITIONS COMPRISING STARCH AND POLYSACCHARIDE ESTERS

APPLICANT(S) FOR DO/EO/US

Catia Bastioli, Roberto Lombi, Matteo Nicolini, Maurizio Tosin and Francesco Degli Innocenti

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
  - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ has been transmitted by the International Bureau.
  - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
  - a. ☒ are transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ have been transmitted by the International Bureau.
  - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
  - d. ☐ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)). (Unexecuted)
11. ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 20 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☒ Certificate of Mailing by Express Mail
20. ☒ Other items or information:

- 1) Transmittal letter;
- 2) One check totalling \$495.00 to cover the filing fee for patent appln.
- 3) Notice Informing the Applicant of the Communication of the International Application to the Designated Offices (Form PCT/IB/308 (July 1996));
- 4) Information Concerning Elected Offices Notified of Their Election (Form PCT/IB/332 (September 1997));
- 5) Notification of Transmittal Of the International Preliminary Examination Report (Form PCT/IPEA416 (July 1992));
- 6) Notification of Transmittal of the International Search Report (Form PCT/ISA/220 (July 1996)); and
- 7) Return postcard

- 21) Applicants claim small entity status under 37 CFR Section 1.9 and 37 CFR Section 1.27.

Page 2 of 2

09/786189

Docket No.: 13929/122995

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re National Application of : )  
 Catia Bastioli, Roberto Lombi, Matteo Nicolini, )  
 Maurizio Tosin and Francesco Degli Innocenti )  
 International Appln. No. PCT/EP99/06390 )  
 International Filing Dated: 31 August 1999 )

Filed Concurrently Herewith On March 1, 2001

For: **BIODEGRADABLE COMPOSITIONS  
 COMPRISING STARCH  
 AND POLYSACCHARIDE ESTERS**

CERTIFICATE OF EXPRESS MAILING


"Express Mail" Mailing Label No.: EL715972942US

Date of Deposit: March 1, 2001

I hereby certify that the following:

- [x] This Certificate of Express Mailing
- [x] Transmittal Letter (Form PTO-1390) in duplicate (2 pp.)
- [x] Published International Application (17 pp.)
- [x] Unexecuted Declaration and Power of Attorney (Form PTO/SB/01) (5 pp.)
- [x] International Search Report (3 pp.)
- [x] Preliminary Amendment (3 pp.)
- [x] Check in the amount of \$495.00 to cover filing fee
- [x] PCT Request (4 pp.)
- [x] PCT Demand (4 pp.)
- [x] Notice Informing The Applicant Of The Communication Of The International Application To The Designated Offices (Form PCT/IB/308) (2 pp.)
- [x] Information Concerning Elected Offices Notified Of Their Election (1 p.)
- [x] Notification of Transmittal of the International Preliminary Examination Report (Form PCT/IPEA/4169) (22 pp.)
- [x] Notification of Transmittal of the International Search Report or Declaration (Form PCT/ISA/220) (7 pp.)
- [x] Information Disclosure Statement (2 pp.)
- [x] PTO-1449 Form to Information Disclosure Statement including references
- [x] Return postcard

are being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR Section 1.10 on the Date of Deposit indicated above in an envelope addressed to the Commissioner for Patents, Box PCT, Washington, D.C. 20231.

  
 Gregory Small

BRYAN CAVE LLP  
 245 Park Avenue  
 New York, New York 10167-0034  
 (212) 692-1800

Express Mail Label No. EL715972942US  
Docket No.: 13929/122995

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re National Application of :

Catia Bastioli, Roberto Lombi, Matteo Nicolini,

Maurizio Tosin and Francesco Degli Innocenti

International Appln. No. PCT/EP99/06390

International Filing Dated: 31 August 1999

Filed Concurrently Herewith On March 1, 2001

For: **BIODEGRADABLE COMPOSITIONS  
COMPRISING STARCH AND  
POLYSACCHARIDE ESTERS**

New York, New York  
March 1, 2001

**PRELIMINARY AMENDMENT**

Commissioner for Patents  
Box PCT  
Washington, DC 20231

Sir:

Please amend the above-identified application as follows:

**In The Claims**

Please substitute the attached annexes to the International Preliminary  
Examination Report for pages 13-16 of the published PCT Application WO 00/12616.

Please amend claims 3, 4, 6, 7, 9, 11, 12, 13 and 14 as follows:

Claim 3, line 1, delete "according to Claim 1 or 2" and insert --according to  
claim 1--.

Claim 4, lines 1 and 2, delete “according to any preceding Claim” and insert  
--according to claim 1--.

Claim 6, lines 1 and 2, delete “according to any one of Claims 1 to 5” and insert  
--according to claim 1--.

Claim 7, lines 1 and 2, delete “according to any one of Claims 1 to 6” and insert  
--according to claim 1--.

Claim 9, lines 1 and 2, delete “according to any one of Claims 1 to 8” and insert  
--according to claim 1--.

Claim 11, lines 1 and 2, delete “according to any one of Claims 1 to 8” and insert  
--according to claim 1--.

Claim 12, lines 1 and 2, delete “according to any one of Claims 1 to 11” and insert  
--according to claim 1--.

Claim 13, lines 1 and 2, delete “according to any one of Claims 1 to 12” and insert  
--according to claim 1--.

Claim 14, line 2, delete “Claims 1 to 13” and insert --claim 1--.

**Remarks**

Claims 3, 4, 6, 7, 9, 11, 12, 13 and 14 have been amended to eliminate multiple dependency and thereby minimize claim fees.

Respectfully submitted,

By: Maurice B. Stiefel

Maurice B. Stiefel

Registration No. 18,479

BRYAN CAVE LLP

245 Park Avenue

New York, NY 10167

Tel No. (212) 692-1838

Fax No. (212)692-1900

09796189-060604  
T09090" 68T99260

ART 34 AND 1

PTO/PCT Rec'd 01 MAR 2001

09/786189

1

Biodegradable compositions comprising starch and polysaccharide esters

The present invention relates to biodegradable compositions comprising starch and polysaccharide esters, suitable for producing moulded articles which can decompose rapidly during composting.

It is reported in the literature that thin cellulose acetate films are rapidly degradable; however, the time required for the biodegradation of thick films or of articles with thick walls is extremely long. For example, two months are required to degrade less than 60% of a thick film.

The problem to be solved in the case of compositions containing starch and cellulose esters consists of the provision of compositions having good biodegradability which are suitable for the production of shaped articles having an adequate capacity to decompose during composting.

Compositions comprising starch and cellulose esters which have improved compatibility between the polymeric components but which do not have adequate biodegradability are described in the patent literature.

For example, EP-A-0 722 980 describes compositions in which the starch and the cellulose ester are rendered more compatible with one another with the use of specific phase compatibilising agents which are selected from various classes of polymeric substances, and which - in addition to improving compatibility - also have the effect of improving biodegradability by virtue of the high level of dispersion conferred on the starch in the cellulose-ester matrix.

However, articles produced from the compositions still have too low a decomposition rate during composting.

It has now surprisingly been found that it is possible considerably to increase the biodegradability of articles produced from compositions comprising partially or completely destructured and/or complexed starch and polysaccharide esters, preferably cellulose esters, and consequently their ability to decompose during composting.

The decomposition times for the articles produced can be reduced to less than two months in standard composting conditions.

The subject matter of the invention is defined by the appended claims.

The compositions of the present invention comprising starch and a polysaccharide ester and preferably a cellulose ester or a starch ester are characterised by a microstructure in which the ester constitutes the matrix and the fraction of destructured and/or dispersed starch constitutes the dispersed phase, with a numeric mean dimension of the domains or dispersed particles preferably of less than 1  $\mu\text{m}$ , more preferably less than 0.5  $\mu\text{m}$ ; the compositions contain an additive which can increase and maintain at values of 4 or more the pH of a solution obtained by immersing granules or pellets of the composition in water at ambient temperature for 1 hour with the use of a water:granules (or pellets) ratio of 10:1 by weight.

The term "partially" referred to destructured or complexed starch is used to contemplate the possible presence of a portion of native crystalline starch up to 30% by wt. with respect to the starting starch content.

The additive, which has the above-mentioned capability to control the pH, has the effect of considerably increasing the biodegradability of the compositions by neutralising the acid



resulting from hydrolysis of the cellulose ester in composting conditions. Any substance insoluble in water and having the above-mentioned capability may be a suitable additive.

Examples of additives are carbonates and hydroxides of alkaline-earth metals such as  $\text{CaCO}_3$ ,  $\text{MgCO}_3$ ,  $\text{Mg(OH)}_2$ .  $\text{CaCO}_3$  is the preferred additive.

The compositions comprise starch and the polysaccharide ester plasticised with a plasticizer in a quantity of from 10 to 40% by weight referred to the polysaccharide ester, in a ratio by weight of from 1:0.6 to 1:18, preferably from 1:2 to 1:3.

The pH regulating additive is present in a quantity of from 0.5 to 30%, preferably from 5 to 20%, by weight relative to the weight of the starch and of the plasticised polysaccharide ester.

Quantities greater than 30% by weight may be used without any significant further improvement.

Too large a quantity of additive may have an adverse effect on the mechanical properties of the compositions.

In addition to the plasticizer for the polysaccharide ester phase, the compositions may also comprise a plasticizer for the starch phase, used in a quantity of from 0.5 to 50% by weight, relative to the weight of the starch.

To permit the production of a finely dispersed microstructure as indicated above, further polymeric additives belonging to the following classes may be used:

a) polymers compatible with polysaccharide esters and/or starch, to which aliphatic or polyhydroxylated chains containing from 4 to 40 carbon atoms are grafted,

- b) copolymers of hydroxy-acids and/or diamines with 2-24 carbon atoms with aliphatic or aromatic diisocyanates or with epoxy compounds or anhydrides,
- c) copolymers of aliphatic polyesters, polyamides, polyureas or polyalkylene glycols with aliphatic or aromatic diisocyanates,
- d) polymers compatible with polysaccharide esters and/or starch to which polyols soluble in starch or polymers capable of complexing starch are grafted, and
- e) polymers capable of complexing starch, such as ethylene/vinyl alcohol or ethylene/acrylic acid copolymers, aliphatic polyesters and polyamides.

The additives of type a) are preferably obtained by grafting aliphatic chains derived from vegetable or animal fats such as oleic, lauric, myristic, palmitic, stearic, linoleic, erucic and ricinoleic acids having terminal groups such as carboxyl groups, esters or salts to facilitate the grafting of the chains.

Examples of polymers compatible with the cellulose esters are:

- cellulose esters with various degrees of substitution (DS),
- starch esters with various DS values, such as acetates,
- starch esters with various DS values, such as products of the reaction of starch with ethylene or propylene glycol,
- partially hydrolysed polyvinyl acetate,
- aliphatic polyesters and aliphatic/aromatic copolyesters.

The number of grafted chains is between 0.1 and 100, preferably from 0.2 to 50, more preferably from 0.3 to 20 grafted chains per 100 monomeric units in the polymeric chain.

Examples of additives of type b) and type c) are the copolymers which can be produced from aliphatic polyesters such as polycaprolactones and polyethylene succinates.

Block copolymers between polycaprolactone and an aromatic or aliphatic diisocyanate, such as a caprolactone-urethane copolymer marketed by Goodrich with the trademark Estane, grade 54351 is representative of the copolymers of class b).

The additives are present in quantities of from 0.1 to 20% by weight, preferably from 0.5 to 10%, relative to the sum of the weight of the starch and of the plasticised polysaccharide ester.

In addition to the components indicated above, the compositions of the invention may contain synthetic polymers in a quantity up to 30% by weight, preferably less than 10%, of polyvinyl alcohol, polyvinyl acetate, thermoplastic polyesters such as polycaprolactone, copolymers of caprolactone with isocyanates, polymers of lactic acid, polyethylene or polybutylene and, in general, polyalkylene adipate, sebacate, and azelate.

The starch which is used to prepare the composition is a natural starch extracted from various plants such as maize, wheat, potato, tapioca and cereal starch. The term starch also includes starches with a high amylopectine content ("waxy" starches), starches with a high amylose content, chemically and physically modified starches, starches in which the type and concentration of the cations associated with phosphate groups are modified, starch ethoxylate, starch acetates, cationic starches, hydrolysed starches, oxidised and cross-linked starches.

The final composition contains starch which is partially or completely destructured and/or complexed. As destructured starch is intended starch which has lost its granular structure (that means absence of Maltese crosses which is visible by optical microscopy in polarised light with magnification in the range of 250 - 700 x).

As complexed starch is intended starch showing a band in second derivative FTIR around at  $946 - 947 \text{ cm}^{-1}$  after removal of the cellulose or starch ester in chloroform (with high starch concentrations without extraction of the cellulose or starch ester) or showing also peaks around  $12-13$  and  $20$  of  $2\theta$  ( $2\theta$ ) in X-ray diffraction experiments.

Representative cellulose and starch esters comprise cellulose acetates, propionates and/or butyrates with various degrees of substitution, such as greater than 2 and preferably greater than 2.4. Cellulose acetate with a DS of from 1.5 to 2.5 is preferred.

The plasticizer usable for the cellulose ester is preferably selected from the following compounds:

- glycerol esters with aliphatic acids containing up to 6 carbon atoms, particularly diacetin and triacetin,
- esters of citric acid, particularly trimethyl or triethyl citrate, as well as acetyl-triethyl citrate,
- dialkyl esters of tartaric acid,
- aliphatic-acid esters, lactones and lactides,
- dialkyl esters of aliphatic acids such as those obtained from oxalic, glutaric, adipic, sebacic, suberic, azelaic acids, preferably dibutyl adipate and dibutyl sebacate,
- dialkyl esters of aromatic acids in which the alkyl group contains from 1 to 10 carbon atoms, particularly dimethyl phthalate, diethyl phthalate, methoxyethyl phthalate and ethoxyethyl phthalate.

- polyethylene glycol adipate, glutarate or sebacate,
- alkyl and aryl phosphates, particularly triethyl and tricresyl phosphates,
- alkyl esters of fatty acids such as butyl oleate,
- polymeric plasticizers such as the products marketed under the trademarks Paraplex by Rohm and Haas, Admex by Arche Daniels Midland, and Flexol by Union Carbide,
- mixed aliphatic-aromatic esters of trimethylol propane and pentaerythritol, polyethylene glycols with alkyl phosphate termination.

The preferred plasticizers are those which act as plasticizers both for the starch phase and for the cellulose ester phase. Acetins belong to this preferred class.

The plasticizers for the starch comprise water, glycerol, glycerol ethoxylate, ethylene glycol or propylene glycol, polyethylene glycol, polypropylene glycol, 1,2-propandiol, 1,3-propandiol, 1,2-, 1,3-, 1,4-butanediol, 1,6-, 1,5-hexanediol, sorbitol diethoxylate, and trimethylolpropane monoethoxylate.

The starch is normally plasticised directly during the mixing stage in a mixture with all of the other components. However, it is also possible to use a two-stage method in which the starch phase and the cellulose phase are plasticised separately.

The preparation of the composition of the invention comprises the mixing of the components in a heated extruder or in any closed container which can ensure conditions of temperature and of shear stress adequate to render the starch and cellulose ester components compatible with one another from a rheological point of view, operating at a temperature of between 80 and 210°C in the presence of water and plasticizers.

The preferred method of preparing the compositions comprises:

- a first step consisting in passing the components through an extruder with times spent in the extruder of the order of from 2 to 50 seconds, during which the starch and the cellulose ester are subjected to bulking under the effect of the plasticizer and possibly of added water, operating at a temperature of between 80 and 180°C,
- a mixing step, during which the mixture of the previous step is subjected to shear stress conditions suitable in particular for rendering the viscosities of the molten cellulose ester and starch similar, if the starting viscosities are different,
- an optional degassing step to produce a molten mass with a water content of less than 6% by weight which ensures, amongst other things, that bubbles do not form in the extruded product. If expanded materials are to be produced, the water content may be higher than 6% and may reach 18-20% by weight.

The resulting molten material is extruded to form pellets from which articles are produced by means of any conventional technique, or the composition may be extruded directly to produce moulded or injection-moulded articles.

The compositions of the present invention are suitable for the production of foams, foamed extruded containers, foamed extruded sheets, moulded foams, injection-moulded articles such as toys and disposable cutlery and, in general, articles for any use which requires decomposition times no longer than two months during composting. The following examples are provided for illustrative purposes and not for limiting the scope of the invention.

#### Examples

Examples 1-4 are comparative examples; Examples 5-7 are in accordance with the invention.

(A) Mixing

The compositions of the examples were prepared with the use of a twin-screw APV extruder model 2030 with a diameter of 30 mm and with L:D=25. The temperature profile of the sixteen controlled-temperature zones was as follows:

60°C x 1 - 100°C x 1 - 180°C x 14.

The rate of rotation of the screw was 120 rpm.

(B) Injection moulding

The pellets produced by the extruder were supplied to a Sandretto Series 60 injection press to produce shaped test samples. The samples were examined with regard to their surface quality by optical microscopy or by SEM electron microscopy.

The samples were also tested to determine the biodegradation rate.

The results of the tests are given in Tables 1 and 2.

TABLE 1

	Ex.1	Ex.2	Ex.3	Ex.4	Ex.5	Ex.6	Ex.7
Aceplast LS (trademark)	75	44	30.5	44	38	40	40
CAB (trademark)			30.5				
Diacetin	25			16	14	14.7	14.7
Epoxydised soya bean oil		16	11.1				
Maize starch		32	22.2	27	25	26.3	26.3
Acetylated starch with DS = 1.3					5		
Sorbitolene (sorbitol ethoxylate)		7.8	5.4	7.8	7.8	8.2	8.2
Erucamide		0.2	0.14	0.2	0.2	0.2	0.2
SAC DS 1.3/laurate 4.6				5			
SAC DS 1.1/laurate 3.2					5		
Calcium carbonate					5	11.6	
Magnesium hydroxide							
Clay							11.6
Footnotes	a	b	c	a,d	d	a,d	a,d

In table 1, the amounts of the components are in percent by weight.

(a) the material was tested for biodegradability (the results are given in Table 2)

(b) the test sample underwent severe delamination

(c) the test sample tended to delaminate

(d) the surface of the sample appeared homogeneous without apparent flakes.

All of the samples which had surface characteristics (d) had a microstructure, according to SEM, in which the dispersed starch phase was in the form of domains at least 80% of which had a numeric mean dimension of less than 0.3  $\mu\text{m}$ .

#### LEGEND

1) Aceplast LS (trademark) is a cellulose acetate with a degree of substitution of 2.5, marketed by Società Acetati S.p.A., of Verbania, Italy.

2) CAB is a cellulose butyrate/acetate marketed by Eastman Chemicals under the trademark CAB 831-20.

3) Acetylated starch with DS = 1.3 is produced by National Starch and is referred to as "78-0403 GDS-1233".

4) The additives indicated in the table were produced from starch acetate (SAC) with DS 1.3 and 2.1, by grafting lauryl radicals in quantities of 4.2 and 3.2 radicals per 100 monomeric units of SAC.

The grafting was carried out with the use of lauric acid chloride in dimethyl acetamide.



After neutralisation with pyridine, the compatibilising agent was precipitated with ethyl ether.

### Biodegradability of the compositions

The biodegradability was tested by recording the loss of weight of the samples which were enclosed in a polypropylene net (with 1 mm mesh) and were incorporated in a substrate of an aged compost with 55% humidity and heated to 50°C in an incubator. A plurality of samples was loaded, that is, one sample per net so that the course of the degradation over time could be followed. For each sample, 50 g of compost was used. The results are given in Table 2.

TABLE 2

Percentage loss of weight undergone by the samples after 15, 60 and 150 days

Examples	15 days	60 days	150 days
1	18.6	23.1	26.3
4	29.8	39.1	51.7
6	40.0	>90.0	completely degraded
7	50.0	>90.0	completely degraded

CLAIMS

1. Biodegradable heterophase compositions comprising partially or completely destructured and/or complexed starch, a polysaccharide ester, and a plasticizer for the polysaccharide ester, in which the polysaccharide ester constitutes the matrix and the starch the dispersed phase, characterised in that the compositions comprise starch and plasticised polysaccharide ester in a ratio by weight of from 1:0.6 to 1:18, the polysaccharide ester is plasticised with a plasticizer in a quantity of from 10 to 40% by weight referred to the polysaccharide ester and the starch is in the form of particles or domains of numeric mean dimension lower than 1  $\mu\text{m}$  for at least 80% of the particles, the compositions comprising an additive which can increase and maintain at values of 4 or more the pH of a solution obtained by placing the compositions in pellet or particle form in contact with water at ambient temperature for 1 hour with the use of a pellet/particles:water ratio of 1:10 by weight.
2. Biodegradable compositions according to Claim 1, in which the polysaccharide ester is a cellulose or a starch ester.
3. Biodegradable compositions according to Claim 1 or 2, in which the particles or domains of the dispersed phase have dimension lower than 0.5  $\mu\text{m}$ .
4. Biodegradable compositions according to any preceding Claim, in which the pH regulating additive is selected from carbonates and hydroxides of alkaline-earth metals.
5. Biodegradable compositions according to Claim 4, in which the pH regulating additive is selected from calcium and magnesium carbonates.

6. Biodegradable compositions according to any one of Claims 1 to 5, in which the polysaccharide ester is a cellulose acetate with a degree of substitution of from 1.5 to 2.5.

7. Biodegradable compositions according to any one of Claims 1 to 6, in which the pH regulating additive is present in a quantity of from 0.5 to 30% by weight relative to the weight of the starch and of the plasticised cellulose ester.

8. Biodegradable compositions according to Claim 7, in which the pH regulating additive is present in a quantity of from 5 to 20%.

9. Biodegradable compositions according to any one of Claims 1 to 8, comprising a further polymeric additive selected from the group consisting of:

- polymers or copolymers compatible with the polysaccharide ester, grafted with aliphatic or polyhydroxylated chains containing from 4 to 40 carbon atoms,

- copolymers obtained from hydroxy-acids and diamines with 2-24 carbon atoms, aliphatic polyesters, polyamides, polyureas and polyalkylene glycols with aliphatic or aromatic diisocyanates,

- copolymers produced from polymers compatible with the polysaccharide esters by grafting polyols soluble in starch.

10. Biodegradable compositions according to Claim 9, in which said further polymeric additive is used in a quantity of from 0.1 to 20% by weight relative to the weight of the starch and of the plasticised cellulose ester.

11. Biodegradable compositions according to any one of Claims 1 to 8, in which the further polymeric additive is se-

lacted from the group consisting of a polymer or copolymer compatible with the cellulose ester grafted with a fatty acid selected from oleic, lauric, palmitic, stearic, erucic, linoleic and ricinoleic acids and a block copolymer between polycaprolactone and an aliphatic or aromatic diisocyanate.

12. Biodegradable compositions according to any one of Claims 1 to 11, comprising a plasticizer for the starch phase, used in a quantity of from 0.5 to 50% relative to the weight of the starch.

13. Biodegradable compositions according to any one of Claims 1 to 12, in which the ratio of plasticised cellulose-ester:starch is between 2:1 and 3:1 by weight.

14. Manufactured articles produced from the compositions of Claims 1 to 13.

15. Manufactured articles according to Claim 14, suitable for the production of foams, foamed extruded containers, foamed extruded sheets, moulded foams.

16. Use, in a biodegradable heterophase composition comprising partially or completely destructured and/or complexed starch, a polysaccharide ester, and a plasticizer for the polysaccharide ester, in which the polysaccharide ester constitutes the matrix and the starch the dispersed phase in the form of particles or domains having an average numeral size lower than 1  $\mu\text{m}$  for at least 80% of the particles, of an additive which can increase and maintain at values of 4 or more the pH of a solution obtained by placing said composition in pellet or particle form in contact with water at ambient temperature for 1 hour, in a pellet (or particle)/water ratio of 1:10 by weight, to increase the biodegradability of articles produced from said compositions.

23-10-2000

EP 009906390

15

17. A method for increasing the biodegradability of articles produced from biodegradable heterophase compositions comprising partially or completely destructured and/or complexed starch, a polysaccharide ester and a plasticizer for the polysaccharide ester, in which the polysaccharide ester constitutes the matrix and the starch the dispersed phase, in form of particles or domains having an average numeral size lower than 1  $\mu\text{m}$  for at least 80% of the particles, comprising adding to said composition an additive which can increase and maintain at values of 4 or more the pH of a solution obtained by placing the compositions in pellet or particle form in contact with water at ambient temperature for 1 hour with a pellet (or particle)/water ratio of 1:10 by weight.

09786189-060601

Docket No.: (C13929/122995) .....

U.S. Serial No.: 09/786,189

DECLARATION AND POWER OF ATTORNEY  
FOR UTILITY PATENT APPLICATION - JOINT

As the below named inventors, we hereby declare that:

Our residences, post office addresses, and  
citizenships are as stated below next to our names.

We believe that we are the original, first, and joint  
inventors of the subject matter which is claimed and for which  
a patent is sought on the invention entitled "Biodegradable compositions  
comprising starch and polysaccharide esters"., the specification of  
which is attached hereto.

We hereby state that we reviewed and understand the  
contents of the above-identified specification, including the  
claims, as amended by any amendment referred to above.

We acknowledge the duty to disclose information that  
is material to the examination of this application in  
accordance with 37 Code of Federal Regulations § 1.56.

We hereby claim foreign priority benefits under 35  
United States Code §§ 119 and 365 of any foreign  
application(s) for the patent or inventor's certificate listed  
below and have also identified below any foreign application  
for patent or inventor's certificate having a filing date  
before that of the application on which priority is claimed:

Prior Foreign Applications: ITALY - No. T098A000735 .....  
... filed on September 1, 1998 .....

We hereby appoint the following attorneys to prosecute  
this application and to transact all business in the Patent  
and Trademark Office connected therewith:

Maurice B. Stiefel, Reg. No. 18,479; Marc S. Gross,  
Reg. No. 19,614; Lawrence G. Kurland, Reg. No. 24,895;  
Stephen P. Gilbert, Reg. No. 27,893; Joseph E. Root, III, Reg.  
No. 30,678, Elizabeth M. Barnhard, Reg. No. 31,088, and Birgit  
E. Morris, Reg. No. 24,484.

Address all telephone calls to ..... at  
telephone number (212) 692-1800.

Address all correspondence to:

.....  
Bryan, Cave, McPheeters & McRoberts  
245 Park Avenue  
New York, New York 10167

09786189-060601

We hereby declare that all statements made herein of our own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

1-0 Full Name of First Inventor: Catia BASTIOLI

Inventor's signature: *Catia Bastioli*

Date: Novara (Italy) March 21, 2001

Residence: I-28100 NOVARA (Italy)

Citizenship: Italian

Post Office Address: Via della Noce, 63 I-28100 NOVARA (Italy)

2-0 Name of Second Joint Inventor: Roberto LOMBI

Inventor's signature: *Roberto Lombi*

Date: Novara (Italy) March 21, 2001

Residence: I-28100 NOVARA (Italy)

Citizenship: Italian

Post Office Address: Via Fara, 51 I-28100 NOVARA (Italy)

3-0 Full Name of Third Joint Inventor, if any: Matteo NICOLINI

Inventor's signature: *Matteo Nicolini*

Date: Novara (Italy) March 21, 2001

Residence: I-28012 CRESSA (Novara) Italy

Citizenship: Italian

Post Office Address: Via Borgomanero, 82 I-28012 CRESSA (Novara) Italy

4-0 Full Name of Fourth Joint Inventor, if any: Maurizio TOSIN

Inventor's signature: *Maurizio Tosin*

Date: Novara (Italy) March 21, 2001

Residence: I-13037 SERRAVALLE SESIA (Vercelli) Italy

Citizenship: Italian

Post Office Address: Via San Giacomo, 6 I-13037 SERRAVALLE SESIA (Vercelli) Italy

5-0  
Full Name of Fifth Inventor, if any: Francesco DEGLI INNOCENTI

Inventor's signature: *Francesco Degli Innocenti*

Date: Novara (Italy), March 21, 2001

Residence: I-28100 NOVARA (Italy)

Citizenship: Italian

Post Office Address: Corso Torino, 16 I-28100 NOVARA (Italy)

Name of Sixth Joint Inventor, if any:

Inventor's signature: .....

Date: .....

Residence:

Citizenship:

Post Office Address:

Full Name of Seventh Joint Inventor, if any:

Inventor's signature: .....

Date: .....

Residence:

Citizenship:

Post Office Address:

Full Name of Eighth Joint Inventor, if any:

Inventor's signature: .....

Date: .....

Residence:

Citizenship:

Post Office Address:

09786489-060601